



Technical Data Sheet

Product	Type
---------	------

COOLSURF™ 2105

Metal Processing

2:1 modified Diethanolamide

Application

Coolsurf 2105 is a modified 2:1 amide of diethanolamine and TOFA.

Coolsurf 2105 is useful in formulating soluble, semi-synthetic and synthetic metalworking fluids and cleaners. It is an excellent co-emulsifier providing excellent oxidative stability, good boundary lubrication, high reserve alkalinity and excellent corrosion protection for soluble oils, semi-synthetics, synthetics, cleaners and rust preventives.

Typical Properties

Test	Typical
Appearance	Clear, dark reddish, viscous fluid
Specific gravity at 15.6° C	0.99
pH at 1%	9.0
Total acid number, mg KOH/g	10
Total alkalinity, mg KOH/g	120
Water wt. %	<2

Benefits

- Excellent co-emulsifier
- High reserve alkalinity and low foam
- Boundary lubrication and oxidative stability
- Thickener and viscosity building in water solution
- Dispersible in oil and water

Suggested Formulation Details

- Soluble Oils: 5-8 % as a co-emulsifier, lubricant, corrosion inhibitor and alkalinity source for machining and forming operations
- Semi-Synthetics: 5-8 % as a co-emulsifier, lubricant, corrosion inhibitor and alkalinity source for machining and forming operations
- Synthetics: 5-10 % as a lubricant, corrosion inhibitor and source of reserve alkalinity in machining and forming operations
- Rust Preventives: 5% as a co-emulsifier and rust inhibitor

Storage and Handling

Recommended Maximum Long Term Storage Temperature	Ambient
Recommended Minimum Temperature for Use	Ambient
Flash Point	>190°C COC



TRU Full Circle Additives

Technical Data Sheet

810-776-8440

www.truadditives.com

TRU Full Circle Additives

4302 James P Cole Boulevard Flint, MI 48505

Phone: 1-810-776-8440 Fax 1-810-776-8540

www.truadditives.com

customerservice@truadditives.com

DISCLAIMER: To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given

Coolsurf is a Trademark of TRU Additives, LLC

11/1/2017