



Technical Data Sheet

Product	Type
----------------	-------------

COOLSURF™ 2175

**Metal Processing
Modified primary amine alkanolamide**

Application

Coolsurf 2175 is 2:1 primary amine alkanolamide of a tall oil fatty acid with low viscosity for ease of handling. It can be used 3-25% by weight.

Coolsurf 2175 is an excellent co-emulsifier providing excellent oxidative stability, good boundary lubrication, high reserve alkalinity and excellent corrosion protection for soluble oils, semi-synthetics, synthetics, and cleaners.

Typical Properties

Test	Typical
Appearance	Amber liquid
Specific gravity at 15.6° C	1.0
pH at 1%	10.4
Total base number, mg KOG/g	180
Total acid number, mg KOH/g	28
Viscosity SUS @40° C, cSt	120

Benefits

- Water soluble and dispersible in oil
- Very low foam and high reserve alkalinity
- Good emulsifying properties
- Boundary lubrication
- Non-staining on aluminum
- Excellent hard water stability

Storage and Handling

Recommended Maximum Long Term Storage Temperature	Ambient
Flash Point	>149° C COC



TRU Full Circle Additives

4302 James P Cole Boulevard Flint, MI 48505

Phone: 1-810-776-8440 Fax 1-810-776-8540

www.truadditives.com

customerservice@truadditives.com

DISCLAIMER: To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given