



Technical Data Sheet

Product	Type
----------------	-------------

EZ-MULZ™ 5454

Metal Processing

Emulsifier base for naphthenic base Oil

Application

EZ-Mulz 5454 is an emulsifier base designed to emulsify naphthenic oils with aniline points of 160°F to 185°F.

Based on natural sodium sulfonate, secondary emulsifiers and other components, EZ-Mulz 5454 is ideal for formulating soluble oils.

EZ-Mulz 5454 is free from chlorine, nitrites, phenols and heavy metals.

Typical Properties

Test	Typical
Appearance	Amber, viscous liquid
Specific gravity at 25° C	1.02
Viscosity @ 40° C, cSt	750
Water wt. %	11
Total acid number, mg KOH/g	25
pH at 1%	9.2

Benefits

- Excellent emulsion stability in all naphthenic oils
- Good corrosion protection in for ferrous metals
- Compatible with extreme pressure additives such as chlorinated or sulfurized compounds

Performance

Corrosion on cast iron ships – ASTM D-4627-92
Ratings scale: 0 = no rust and 5 = 100% rust

5% emulsion of 15% EZ-Mulz 5454 in oil.....0

Typical Applications

EZ-Mulz 5454 can be used in several metalworking applications. For example:

Use the following as a guideline, balance formula as needed

General-purpose soluble oil

	<u>% by weight</u>
100 SUS naphthenic oil	65 - 85
EZ-Mulz 5454	15 - 25
Chlorinated additive (Extreme pressure agent).....	0 - 20
Glycol ether (To modify viscosity)	0 - 1
Biocide	0 - 3
Fungicide	0 - 1
Defoamer, if necessary	0 - 1

Adding some biocides may require the addition of tall oil fatty acid to balance the formula.

Storage and Handling

Recommended Maximum Long Term Storage Temperature*	Ambient
Recommended Minimum Temperature for Use	Ambient
Flash Point	>150°C COC

*Do not store with excessive heat (>150° F) over long periods.



TRU Full Circle Additives

Technical Data Sheet

810-776-8440

www.truadditives.com

TRU Full Circle Additives

4302 James P Cole Boulevard Flint, MI 48505

Phone: 1-810-776-8440 Fax 1-810-776-8540

www.truadditives.com

customerservice@truadditives.com

DISCLAIMER: To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given

EZ-Mulz is a Trademark of TRU Additives, LLC

11/1/2017

