



TRU Full Circle Additives

Technical Data Sheet  
810-776-8440  
www.truadditives.com

# Technical Data Sheet

Product	Type
---------	------

**LUBRISTAY™ 9750**                      **Metal Processing  
Oil Soluble Extreme Pressure and Lubricity  
Additive**

## Application

Lubristay 9750 is an oil soluble, potassium triborate extreme pressure and anti-wear additive for industrial oils, greases and gear lubricants. It can be used alone or in combinations with other anti-wear and extreme pressure additives.

Lubristay 9750 will not stain yellow metals and is thermally stable.

## Typical Properties (Not Specifications)

Test	Typical
Appearance	Amber brown viscous liquid
Specific Gravity @25°C	1.12
Boron Content, wt. %	7
Viscosity @ 25° C, cPs	450

Lube and gear oils, greases, metalworking lubricants, industrial oils

## Storage and Handling

Recommended Maximum Long Term Storage Temperature*	Must be ambient. 1 year shelf life. Avoid freezing. Mix prior to use
Flash Point	>150° C



TRU Full Circle Additives

Technical Data Sheet  
810-776-8440  
www.truadditives.com

### TRU Full Circle Additives

4302 James P Cole Boulevard Flint, MI 48505  
Phone: 1-810-776-8440 Fax 1-810-776-8540  
[www.truadditives.com](http://www.truadditives.com)  
[customerservice@truadditives.com](mailto:customerservice@truadditives.com)

**DISCLAIMER:** To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given