



# Technical Data Sheet

<b>Product</b>	<b>Type</b>
----------------	-------------

**LUBRISTAY™ 420**

**Metalworking**

**Very Long Chain Chlorinated Paraffin**

## Application

Lubristay 420 is a formulated very long chain chlorinated paraffin. It is also a proven extreme pressure additive for straight oil and soluble oil metalworking forming operations. Also useful as flame retardant and plasticizer in polymers. Lubristay 420 also acts as a flame retardant, plasticizer and lubricant in adhesives, caulks, sealants and coatings

The C-21 chlorinated paraffin used in Lubristay 420 continues to be approved for this use by the EPA under CAS #1402738-52-6

## Typical Properties

Test	Typical
Color, gardner	2
Specific gravity at 25° C	1.15
Chorine Content, % wt.	40
Viscosity @ 100° C, cSt	35
Viscosity @ 40° C, cSt	700

## Benefits

- Excellent for extreme pressure applications
- Completely soluble in naphthenic and most paraffinic oils
- Low foaming
- Excellent hydrolytic, thermal and oxidative stability

## Suggested Formulation Details

Lubristay is used from 5-50% in the straight or soluble oil concentrate depending on the use:

- Soluble oils for machining 4 – 8%
- Soluble oils for drawing and stamping 5 – 15%
- Straight oils for machining 5 – 15%
- Straining oils for drawing and stamping 10 -40%

## Storage and Handling

Recommended Maximum Long Term Storage Temperature*	Ambient
Recommended Minimum Temperature for Use	Ambient
Flash Point	>100° C COC

\*Long term storage at temperatures above this may result in loss of performance.



### TRU Full Circle Additives

Technical Data Sheet

810-776-8440

[www.truadditives.com](http://www.truadditives.com)

## TRU Full Circle Additives

4302 James P Cole Boulevard Flint, MI 48505

Phone: 1-810-776-8440 Fax 1-810-776-8540

[www.truadditives.com](http://www.truadditives.com)

[customerservice@truadditives.com](mailto:customerservice@truadditives.com)

**DISCLAIMER:** To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given

Lubristay is a Trademark of TRU Additives, LLC

06/01/2021